

# <u>Product ID:</u> RCT 11 1032 EP – HB HS LV Beige Epoxy DTM Primer

### **Product Description & Suggested Uses:**

RCT 11 1032 EP is a two component, epoxy polyamide primer designed for applications where excellent corrosion, chemical, moisture and water barrier properties are required.

#### Benefits Includes:

- Single Coat Direct to Metal High Build
- Low VOC & Very Low HAPS
- Very Good Corrosion Resistance
- Fast Re-coat

#### Typical Uses: Primer for:

- Railcar Exteriors
- Tank Exteriors
- Structural Steel
- Water Towers

#### Mixing and Thinning/Reducing Instructions:

Mix 1 part RCT 11 1032 EP by volume with 1 part RCT 01 1266 AM Hardener. Agitate each component thoroughly before combining. If reducing or thinning is required, please contact your Rapid Cure Technologies (RCT) technical service representative for instructions.

#### **Directions for Use:**

Surface must be clean, dry, sound and free of dirt, dust, grease, oils, residues, waxes, water, foreign particles, and any other contaminants that may interfere with coating adhesion and intimate contact with substrate. Steel surface preparation should meet SSPC-SP6/NACE 3. Metal surface must be 5 degrees above the dew point temperature.

RCT 11 1032 EP is designed to be applied by airless spray, brush or roll. Airless spray @ 2500-4500 psi with 0.017-0.021 tips is recommended. If reduction is required, 5-10% with an RCT recommended solvent may be used after both components are mixed together. Pot life is 6 hours @ 75 degrees and significantly reduced at elevated temperatures. Pot life is extended with reduction.

#### Clean-up:

Clean all equipment immediately after use with MEK or other RCT approved solvents. Use clean solvent only. In case of spill, absorb and dispose of in accordance with local, State, and/or Federal regulations.

## **Technical Data Sheet**

**Document Date:** 02 Feb 2020

#### **Typical Mixed Properties:**

Color Beige, Gray, White, Red, Black

Type Epoxy/Polyamide

Viscosity (25°C) 80-90 KU's Density (25°C) 10.5-11.0 lbs/gal

% Solids (by Volume)
 % Solids (by Weight)
 VOC
 64-66%
 76-78%
 1.6-1.7 lbs/gal

Flash Point 17°F Gloss 10-20°

Recommended DFT

Maximum DFT

Coverage

Dry @ 75 degrees F

4-6 mils (100-150 um)

12 mils (300 um)

1043 ft² @ 1.0 mil

1-2 hrs to touch

3-4 hrs to handle

Recoat @ 75°F 3 hr minimum, 7 day maximum

Pot life @ 75°F 6 hrs

#### Packaging:

RCT 11 1032 EP is available in one 1-gallon cans, five 5-gallon pails, 55-gallon steel drums and totes. For additional packaging options, please contact your local Rapid Cure Technologies representative.

#### Storage & Shelf Life:

Store indoors in original, tightly sealed container out of direct sunlight between 40°F (5°C) and 100°F (38°C), 0% to 90% relative humidity. Warranted shelf life is 12 months from date of manufacture (DOM) in original unopened and properly stored container.

#### **Safety Information:**

Avoid contact with skin and use good ventilation. Wear chemically resistant gloves (nitrile are recommended) and chemical safety glasses. If skin contact is made, wash immediately with soap and water. Do not use solvents to clean skin. Refer to Safety Data Sheet for further safety and handling information.

FOR PROFESSIONAL USE ONLY
NOT FOR RESIDENTIAL USE
KEEP OUT OF REACH OF CHILDREN

RAPID CURE TECHNOLOGIES, INC. | 7030 FLY RD, EAST SYRACUSE, NY 13057 | (888) 847-3610 | WWW.RAPIDCURETECHNOLOGIES.COM